

Description

Archco-Rigidon 403D Flowcoat is a low viscosity Novalac Vinyl Ester resin designed to thin down **403D or 403D Micro** to a sprayable viscosity during cold conditions between 10 and 25°C.

Principal Characteristics

- * Achieves good atomisation when spraying
- * Lessens styrene emission
- * Does not affect chemical resistance

RIGSPRAY	Novalac Vinyl Ester
Operating Temp Range	Min. -50°C to+200°C
Colour	Transparent Light Purple
Catalyst Type	Archco Rigidon c3
Volume Solids	99%
Specific Gravity	1.1
Viscosity	150mPa.s @25°C

Safety

This product contains styrene and is flammable.

Always wear suitable protective clothing including gloves and goggles.

Refer to the relevant 16 point Material Safety Data Sheet.

Suggested Uses

A preferable viscosity reducer for **403D or 403D Micro** rather than using styrene which may affect the strength and chemical resistance of the end product if used in amounts greater than 5%.

403D Flowcoat may be used up to 15%

Contact **Archco-Rigidon** Engineers for further information.