

## DENSO BUTYL PRIMER

**DESCRIPTION** A fast drying butyl rubber based primer for all surfaces prior to the application of the Denso S43 Innerwrap, Denso S130 P and butyl extrusions.

**COMPOSITION** Butyl Rubber combined with adhesive resins in solvent.

TYPICAL PROPERTIES	TEST METHOD	DATA
Colour:		Black
Specific Gravity:	ASTM 1298	0.79
Viscosity	ASTM D 1200	35 sec
Volume Solids	ISO 1515	27%
Converting Capacity (To Steel)		6m <sup>2</sup> /lt
Wet Film Thickness		160 - 220 Micron
Dry Film Thickness		45 - 60 Micron
Drying Time		8 min @ 23°C
Flash Point	ABEL IP 170	-12°C
Application Temperature Range		- 30°C - 60°C