

SYLBOND TS200 WATERPROOFING MEMBRANE

DESCRIPTION	Denso Sylbond TS200 Waterproofing Membrane is a unique, heavy duty, cold applied, self-adhesive, reinforced waterproofing membrane, specially developed to facilitate instant tiling after waterproofing has been completed. Denso Sylbond TS200 Waterproofing Membrane provides complete protection from water exposure to the substrate, as well as preventing leakages.
USES	<ul style="list-style-type: none">- Provides instant waterproofing / tiling of balconies and areas to be tiled- Recommended as a tiling substrate (ie. Tile directly onto the mesh with recommended tile adhesive)- Facilitates immediate tiling after membrane is laid (no lost time)
COMPOSITION	The membrane consists of a woven glass fibre grid, laminated to a pressure sensitive, reinforced, modified bitumen compound. The rolls are interleaved with a disposable release film.
FEATURES	<ul style="list-style-type: none">- The mesh is off-set during manufacturing- This creates a selvage of pure polymer modified bitumen adhesive down the length of one side of the top of the roll.- This will amalgamate by the process of cold fusion, with the underside of the adjacent overlapping sheet.
APPLICATION	Tiles are applied using a conventional tile adhesive which initially keys to the mesh. As the tile adhesive dries, it forms a strong permanent bond through the mesh directly onto the waterproofing layer
SAFETY	Normal hygiene procedures. Wash hands thoroughly with soap and water or a proprietary hand-cleaner prior to eating or smoking. Launder contaminated clothing, gloves, etc.
STORAGE	Store in original containers in a cool dry place. Maximum recommended shelf life : 6 months.



SYLBOND TS200 WATERPROOFING MEMBRANE (cont.)

TYPICAL PROPERTIES	TEST METHOD	DATA
Breaking Strength	ASTM D1000	6N/mm
Elongation @ Break	ASTM D1000	15%
Adhesion <ul style="list-style-type: none">- To Primed Steel- To Self	ASTM D1000 24hr ASTM D1000 24hr	2.5 N/mm 2.5 N/mm
Resistance to Acids, Alkalis & Salts		Excellent
Temperature Range <ul style="list-style-type: none">- For application- For Service		+15C to 45C +5C to 65C
Length		15m
Width		1000mm
Core Size		76mm I.D
Thickness		2mm
Weight		2Kg/m ²
Coverage per roll		14 m ²
Recommended Primer		Denso Bitumen Primer D

Important

Winn & Coales / Denso SA (Pty) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request.

Denso SA (Pty) Ltd operate a Quality Management System registered to ISO 9001:2008.

Head Office / Factory: 120 Malacca Road, Red Hill, Durban. P.O.Box 201259, Durban North, 4016, South Africa
Tel: +27 (031) 569 4319 Fax: +27 (031) 569 4328 Email: bid@denso.co.za Website: www.denso.co.za