

CLADSEAL 300

DESCRIPTION	A general purpose insulator between cladding, roof sheets and purlins to prevent Galvanic Corrosion and Vibration.
COMPOSITION	A tough white medium density polyethylene backing film, laminated to a pressure sensitive adhesive.
SAFETY	Normal hygiene procedures. Wash hands thoroughly with soap and water or a proprietary hand-cleaner prior to eating or smoking. Launder contaminated clothing, gloves, etc.
STORAGE	Store in original containers in a cool dry place. Maximum recommended shelf life : 6 months.

TYPICAL PROPERTIES	TEST METHOD	DATA
Tensile Strength	ASTM D1000	15 Mpa min
Elongation at break	ASTM D1000	>350%
Thickness <ul style="list-style-type: none">• Backing film• Adhesive	ASTM D1000	300μ 20μ
Adhesion to self	ASTM D1000	0.04N/mm
Dielectric strength	ASTM D1000	20Kv min
Roll Widths	ASTM D1000	50mm, 75mm, 100mm, 150mm (or to order)
Roll Length	ASTM D1000	50m (or to order)
Colours		White

Important

Winn & Coales / Denso SA (Pty) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request.

Denso SA (Pty) Ltd operate a Quality Management System registered to ISO 9001:2008).